

Kane Ace™ MX

Product properties

Matrix Resin System	Grade name	Dispersed CSR type*	%CSR	Nominal Viscosity	Nominal EEW
unit of measure			wt%	cps	g/eq
Bis A Epoxy	MX-125	SBR	25 +/- 1	5,500 @ 50°C	243
	MX-150	PBR	40 +/- 1	16,000 @ 50°C	310
	MX-153	PBR	33 +/- 1	17,000 @ 50°C	270
	MX-154	PBR	40 +/- 1	25,000 @ 50°C	301
	MX-156	PBR	25 +/- 1	4,500 @ 50°C	243
	MX-257	PBR	37 +/- 1	18,000 @ 50°C	297
	MX-171	other	30 +/- 1	22,000 @ 50°C	260
	MX-962	SIL	25 +/- 1	3,000 @ 50°C	243
	Bis F Epoxy	MX-135	SBR	25 +/- 1	13,000 @ 50°C
MX-136		PBR	25 +/- 1	2,500 @ 50°C	217
MX-267		PBR	37 +/- 1	7,000 @ 50°C	269
Multi-Functional TGMDA Epoxy	MX-414	PBR	25 +/- 1	30,000 @ 50°C	149
Multi-Functional TGPAP Epoxy	MX-451	SBR	25 +/- 1	12,000 @ 50°C	132
Phenol Novolac Epoxy	MX-217	PBR	25 +/- 1	10,000 @ 50°C	231
Cycloaliphatic Epoxy	MX-553	PBR	30 +/- 1	3,000 @ 50°C	192
Polypropylene Glycol 1000 Mw	MX-710	PBR	40 +/- 1	3,000 @ 25°C	(OHV) 68
Polypropylene Glycol 400 Mw	MX-714	PBR	40 +/- 1	2,000 @ 25°C	(OHV) 170
Radical Curable Resin (for UP/VE)	MX-010	PBR	40 +/- 1	6,000 @ 25°C	-

***CSR type:**

SBR: Styrene-Butadiene Rubber

PBR: Polybutadiene Rubber

SIL: Silicone Rubber

Other

Above data are for product selection only. All technical statements, information and recommendations in this catalogue are based on tests and data, which are reliable to the best of Kaneka's knowledge. Due to possible variations of conditions and processing methods beyond our control, no guarantees or warranties are expressed or implied as to use, handling or processing of Kane Ace™. There is no warranty of merchantability

and fitness for particular purpose. No suggestions are made in the catalogue whatsoever for infringement of any patents. We expressly disclaim liabilities for any damage, arising from the use, handling or processing of Kane Ace™, as well as for the consequences, whether or not Kane Ace™ has been used, or is alleged to have been used, in accordance with the instructions given in the catalogue.

Kane Ace™ MX

Contact: Akio Taniguchi | Senior Business Manager MX

Tel. +32 (0) 474 941 687 | E-mail: info.mx@kaneka.be